

THE SUPERCONDUCTIVITY OF $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ REACTED WITH NANO-SiC

W.N.A.W. Shaaidi, K.P. Lim, K.A. Matori, E. Saion,
S.A. Halim and S.K. Chen

*Physics Department, Faculty of Science, Universiti Putra Malaysia,
43400 UPM Serdang, Selangor Darul Ehsan, Malaysia.*

Corresponding author: one_ain@yahoo.com

ABSTRACT

We report on the influence of nano-SiC as an additive on the superconductivity of polycrystalline $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ (YBCO) prepared via solid state reaction method. In particular, we studied the characteristic of superconducting transition temperature (T_c), crystal structure and microstructure of the YBCO system. X-ray diffraction patterns show the dominance of YBCO (123) phase in all the samples. The a and c axes increase slightly while the b -axis decreases with SiC addition causing the reduced orthorhombicity. Measurements of resistance versus temperature show that the normal state changes from metallic to semiconducting like behavior upon increasing the amount of additive from 1.5 wt.% onwards. The $T_{c\text{-onset}}$ was found to decrease from 91 K for pure samples to 78 K for the 2 wt. % sample attributable to the adverse effect of Si. The broadening in superconducting transition breadth, ΔT indicates degraded crystallinity or inhomogeneity in the samples caused by SiC additions.

Keywords: YBCO; lattice parameters; superconducting transition temperature

REFERENCES

- [1]. D. Dimos, P. Chaudhari and J. Mannhart, *Phys. Rev. B* **41** (1990) 4038-4049.
- [2]. X.U. Sheng, Y. Aiping, G.U. Yangni, W.U. Xiaoshan, *Journal of Rare Earth*, **28** (2010) 434-436.
- [3]. Z.H. He, T. Habisreuther, G. Bruchlos, D. Litzkendorf, W. Gawalek, *Physica C* **356** (2001) 277-284
- [4]. A. Mellekh, M. Zouaoui, F. B. Azzouz, M. Annabi, M. B. Salem, *Solid State Communications* **140** (2006) 318-323.
- [5]. Z.Q. Yang, X.D. Su, C. Zhang, G.W. Qiao, W. Han, *Phys. Stat. Sol. (a)* **167** (1998) 165-170.
- [6]. J. Quanli, Z. Haijun, L. Suping, J. Xiaolin, *Ceramics International* **33** (2007) 309-313.
- [7]. R. Giri, V.P.S. Awana, H.K. Singh, R.S. Tiwari, O.N. Srivastava, A.Gupta, B.V. Kumaraswamy, H. Kishan, *Physica C* **419** (2005) 101-108.
- [8]. T.H. Meen, F.L. Juang, W.J. Huang, Y.C. Chert, K.C. Huang, H.D. Yang, *Physica C* **242** (1995) 373-380.
- [9]. N. Ruffer, G. Kaiser and H.R. Khan, *Cryogenics* **33** (1) (1993) 124-128.

- [10]. T. Nakashima, Y. Tazaki, Y. Ishii, S. Horii, J. Shimoyama, and K. Kishio, *IEEE Transactions on Applied Superconductivity*, 17(2) (2007) 2996-2999.
- [11]. I. Bouchoucha, F.B. Azzouz, M. Annabi, M. Zouaoui, M.B. Salem, *Physica C* **470** (2010) 262–268.